

Magnetite Ore Certified Reference Material: Certificate of Analysis

PBS-71

Table 1: PBS-71 Certified Values via fusion XRF (Un-Normalised)

Analyte	unit	Value	Standard Deviation		95% Conf. Int.		Coeff. Of Var.	Number of Labs	Number of Analysis
			1 SD	1 SD Within Lab	lower	upper			
Fe	%	30.70	0.119	0.088	30.61	30.80	0.4%	6	36
SiO2	%	47.22	0.158	0.115	47.11	47.34	0.3%	7	41
Al2O3	%	1.46	0.024	0.013	1.44	1.48	1.6%	7	42
TiO2	%	0.073	0.0036	0.0031	0.070	0.075	5.0%	6	35
Mn	%	0.118	0.0026	0.0010	0.116	0.121	2.2%	7	42
CaO	%	0.496	0.0085	0.0058	0.489	0.502	1.7%	7	42
P	%	0.103	0.0019	0.0009	0.102	0.105	1.8%	8	48
S	%	0.131	0.0016	0.0016	0.130	0.132	1.2%	6	35
MgO	%	2.23	0.024	0.012	2.21	2.26	1.1%	6	36
K2O	%	0.660	0.0119	0.0047	0.649	0.671	1.8%	7	42
Na2O	%	0.153	0.0063	0.0053	0.148	0.157	4.1%	6	36
LOI 1000	%	3.26	0.091	0.044	3.18	3.34	2.8%	7	42

Table 2: PBS-71 Provisional Values via fusion XRF (Un-Normalised)

Analyte	unit	Value	Standard Deviation		95% Conf. Int.		Coeff. Of Var.	No. of Labs	No. of Analysis
			1 SD	1 SD Within Lab	lower	upper			
Cl	%	0.043	0.0042	0.0026	0.038	0.047	9.8%	5	30

Table 3: PBS-71 Informational Values via fusion XRF (Un-Normalised)

Analyte	unit	Value	Number of Labs	Number of Analysis
As	%	0.002	1	4
Ba	%	0.006	5	28
Co	%	0.002	2	7
Cr	%	0.008	5	30
Cu	%	0.001	2	4
Ni	%	0.002	3	17
Pb	%	0.002	1	3
Sn	%	0.002	2	9
Sr	%	0.003	2	12
V	%	0.002	2	8
Zn	%	0.002	2	12
Zr	%	0.004	4	23

Table 4: PBS-71 Certified Values of DTR Magnetite Conc. via fusion XRF (Un-Normalised)

Analyte	unit	Value	Standard Deviation		95% Conf. Int.		Coeff. Of Var.	Number of Labs	Number of Analysis
			1 SD	1 SD Within Lab	lower	upper			
Fe	%	62.20	0.900	0.412	61.48	62.92	1.5%	8	48
SiO2	%	11.53	0.975	0.374	10.72	12.33	8.5%	8	48
CaO	%	0.151	0.0119	0.0052	0.141	0.160	7.9%	8	48
P	%	0.038	0.0029	0.0013	0.036	0.041	7.7%	8	48
LOI 1000	%	-1.76	0.141	0.082	-1.65	-1.86	8.1%	8	48
Distr Mags Pc*	%	34.38	1.3	0.626	33.35	35.40	3.8%	8	47

*Via Davis Tube Recovery at defined parameters

Table 5: PBS-71 Provisional Values of DTR Magnetite Conc. via fusion XRF (Un-Normalised)

Analyte	unit	Value	Standard Deviation		95% Conf. Int.		Coeff. Of Var.	No. of Labs	No. of Analysis
			1 SD	1 SD Within Lab	lower	upper			
Al2O3	%	0.30	0.039	0.018	0.27	0.33	12.9%	8	48
TiO2	%	0.031	0.0061	0.0036	0.025	0.036	20.1%	7	42
S	%	0.019	0.0032	0.0023	0.016	0.021	17.4%	6	36
MgO	%	0.497	0.0503	0.0228	0.456	0.537	10.1%	8	48
K2O	%	0.126	0.0207	0.0075	0.108	0.143	16.5%	8	48
Na2O	%	0.028	0.0063	0.0054	0.023	0.032	22.8%	6	36
Cr	%	0.017	0.0015	0.0003	0.015	0.019	8.7%	5	30
V	%	0.004	0.0005	0.0005	0.004	0.004	12.9%	4	24

Table 6: PBS-71 Informational Values of DTR Magnetite Conc. via fusion XRF (Un-Normalised)

Analyte	unit	Value	Number of Labs	Number of Analysis
Mn	%	0.027	8	48
As	%	BDL	1	-
Ba	%	0.004	3	16
Cl	%	0.005	4	21
Co	%	0.001	2	11
Cu	%	0.002	3	17
Ni	%	0.003	3	18
Pb	%	0.004	3	17
Sn	%	0.001	2	10
Sr	%	0.002	2	11
Zn	%	0.002	3	18
Zr	%	0.005	3	17

Table 7: PBS-71 Certified Particle Size Distribution Values via Laser Diffraction Analysis.

Analyte	unit	Value	Standard Deviation		95% Conf. Int.		Coeff. Of Var.	No. of Labs	No. of Analysis
			1 SD	1 SD Within Lab	lower	upper			
P90	um	47.1	2.31	1.46	45.3	48.9	4.9%	7	21
P80	um	33.8	1.89	0.91	32.4	35.2	5.6%	8	24
P50	um	12.2	0.96	0.32	11.5	13.0	7.8%	8	24

Table 8: PBS-71 Provisional Particle Size Distribution Values via Laser Diffraction Analysis.

Analyte	unit	Value	Standard Deviation		95% Conf. Int.		Coeff. Of Var.	No. of Labs	No. of Analysis
			1 SD	1 SD Within Lab	lower	upper			
P10	um	1.6	0.16	0.08	1.5	1.8	10.1%	6	18

Table 9: PBS-71 Certified Particle Size Distribution Values via Wet Sieve Analysis.

Analyte	unit	Value	Standard Deviation		95% Conf. Int.		Coeff. Of Var.	No. of Labs	No. of Analysis
			1 SD	1 SD Within Lab	lower	upper			
P90	um	44.1	2.03	1.08	42.3	46.0	4.6%	6	18
P80	um	33.9	2.83	0.88	31.1	36.6	8.4%	6	18

Table 10: PBS-71 Provisional Particle Size Distribution Values via Wet Sieve Analysis

Analyte	unit	Value	Standard Deviation		95% Conf. Int.		Coeff. Of Var.	No. of Labs	No. of Analysis
			1 SD	1 SD Within Lab	lower	upper			
P50	um	17.2	0.52	0.33	16.7	17.8	3.0%	5	15

Version Control				
Doc. Version	Analysis Version	Author	Date	Changes
PBS-71-v6	V3	B. Armstrong	18/3/2022	Correct Distr Mag pc values in Table 4 Include particle size distribution data Table 7 to 10

Introduction

This document specifies preparation, analysis, and certification of reference material PBS-71.

Origin of Material

The source material is from a magnetite mine located in Western Australia.

Method of preparation

The material was prepared as follows:

- Drying at 105°C to constant mass.
- Multistage crushing and milling to target size representative of milling process.
- Homogenisation via high shear blenders. Blended from two similar materials in a relative proportion of 45% / 55% by mass.
- Packaging into sealed 10kg vessels awaiting final packaging at client request.

Samples were taken at intervals during the packaging stage to provide material for the Certification process. The material was tested for:

- XRF / LOI on head (feed).
- Davis Tube Wash.
- XRF / LOI on Davis Tube magnetic concentrate.
- Laser Diffraction Particle Size Analysis on head (feed).
- Wet Screen sieve Particle Size Analysis on head (feed).

Measurement techniques used for certification

XRF Analysis

Eight laboratories were each given 6 x 50g randomly selected samples for analysis of both head sample and magnetite concentrate via lithium borate fusion XRF for the following:

Fe, SiO₂, Al₂O₃, TiO₂, Mn, CaO, P, S, MgO, K₂O, Na₂O, Ba, As, Cu, Pb, Zn, Cl, Co, Cr₂O₃, Ni, Sn, Sr, V, Zr.

Results are quoted as Un-Normalised.

In addition, loss on Ignition (LOI) was requested via Thermal gravimetric analysis (TGA) at 1,000°C only.

Davis Tube Wash

Davis Tube Wash (DTW) was undertaken at eight laboratories with six samples each laboratory. Parameters for DTW were specified as following:

1. No sample preparation required. Use as supplied.
2. Stroke Frequency 60/minute
3. Stroke Length 38 mm
4. Magnetic Field Strength 3000 gauss
5. Tube Angle 45 degrees
6. Tube Diameter 25 mm
7. Washing Time 15 minutes or until water is clear

The concentrate sample is collected in a small container after washing is complete. The concentrate is then vacuum filtered, washed, dried and weighed.

Laser Diffraction Particle Size Distribution Analysis

Laser Diffraction analysis was undertaken at eight laboratories with each laboratory receiving three 50g samples. Analysis was undertaken using instruments from various manufacturers and different models. Guidance to laboratories was restricted to material description as a “pulverised magnetite ore with high silica content”. Results were reported to the 10th, 50th and 80th percentile.

Wet Screen Sieve Particle Size Distribution Analysis

Six laboratories were each provided three samples of between 50g and 200g, according to mass requested. Sieve sizes were requested at 25um, 28um (only when available), 32um, 45um, 53um. Results were commonly reported in microns passing 50th, 80th, and 90th percentile. Where data was not reported to a common percentile, this was calculated prior to Certification using forecast function in excel, and verified against stated results.

Method of Certification

Outlier laboratory and individual analytical results are removed from the informing sample population to remove erroneous values. The system used is:

- Remove below detection values which are imported as negative values. In addition, if laboratory groups of data contain 50% or more below detection values the entire laboratory group of results is discarded from subsequent analysis.
- Remove laboratory groups with modified Z-scores >3.0, using method of Iglewicz and Hoaglin (1993).
- Remove laboratory group data with excessive range which demonstrates out of control processes. This is calculated as laboratory group results standard deviations with Z-score >3.
- Individual outliers with Z-score >3 are then removed from the informing population when confirmed using a $\alpha=0.01$ on a two-tailed Grubbs test on the grouped data.

The above process is reviewed by the Certifying Officer, and in some cases will use their judgment in identifying or eliminating outliers.

Results have been grouped in Certified, Provisional, and Informational on the below general criteria:

- Certified values show good agreement with a low (<10%) coefficient of variation (CoV = Std. Deviation / Mean), a measure of the variability relative to the mean.
- Provisional are CoV 10% to 20%, or with significant disagreement between laboratories which cannot be resolved using statistical review techniques alone.
- Informational values are typically near the detection limit for the analysis. As such conventional standard deviation and confidence intervals are not appropriate controls. In these cases it is likely that more appropriate analysis techniques are required for the analyte concentrations.

The Certified value is calculated from the mean of laboratory means, Standard Deviation is calculated as the standard deviation of all results. Within Laboratory Standard Deviation is calculated from ANOVA of the laboratory grouped results. Between Laboratory Standard Deviation when quoted is calculated according to ISO Guide 35, section B.6.

Confidence Interval is derived at the $\alpha=0.05$ from the Students t-distribution for the number of participating laboratories, and the standard deviation of the laboratory means. The confidence interval is a measure of the reliability of the consensus value. In this case, it is a measure of the reliability of the certified value. For example, a 95% CI for Fe could be interpreted as there is a 0.95 probability that the certified value is between (mean \pm CI). The narrower the interval, the more precise the certified value. A 95% CI is distinct from the lower limit and upper limit at 2SD which provides an estimate of the range of values for 95% of individual measurements for a given analyte. In the case of Fe, approximately 95% of replicates are expected to be between two SDs either side of the certified value.

The above calculations are in accordance with ISO 11459 and ISO Guide 35.

Consensus Values

Summary data of assigned values, standard deviations and confidence intervals, and number of laboratories and analysis used in calculating the values are shown in Table 1, Table 4, Table 7, Table 9, for Certified Values, Table 2, Table 5, Table 8, Table 10 for Provisional Values, and Table 3, Table 6 for Informational Values.

Participating laboratories

Table 11: PBS-71 Participating Laboratories

Laboratory	Location	XRF Analysis	DTR	PSD via Laser Diffn.	PSD via Wet Sieve
ALS Brisbane	Queensland, Australia	Y			
ALS Malaga	Western Australia	y	y	y	Y
BV Wingfield	South Australia	y	y	y	Y
Intertek Genalysis Maddington	Western Australia	y	y		
Nagrom, Kelmscott	Western Australia	y	y	y	y
BV Whyalla	South Australia	y	y	y	
IMO	Western Australia			y	y
ALS Burnie	Tasmania		y		
SGS Metallurgy	Western Australia	y	y	y	y
BV Canning Vale Metallurgy	Western Australia	y	y	y	y
ATA Scientific	New South Wales			y	
Count		8	8	8	6

Preparer and supplier of reference material

The reference material PBS-71 has been prepared and certified, and is certified by:

Pilbara Standards Pty Ltd
16 Durham Rd,
Bayswater,
WA6053,
Australia

www.pilbarastandards.com.au

The material is supplied in 50g sealed mylar bags and 1kg sealed plastic jars.

Intended use

PBS-71 is intended for the monitoring of laboratory performance in the analysis of analytes in geological samples; the verification of analytical methods; and the calibration of instruments used in the determination of the concentration of analytes reported in Table 1 to Table 9.

Stability and storage instructions

PBS-71 is stable in the sealed plastic bags under normal conditions of storage.

Instructions for the correct use of the reference material

The recommended values for PBS-71 refer to the concentration levels after removal of hygroscopic moisture by drying in air to constant mass at 105°C. If the reference material is not dried prior to analysis, the recommended value should be corrected to the moisture bearing basis.

Legal notice

Pilbara Standards Pty Ltd has prepared and statistically evaluated the property values of this reference material to the best of ability. The purchaser by receipt hereof releases and indemnifies Pilbara Standards Pty Ltd from and against all liability and costs from the use of this material and information.

Certifying officer

Bruce Armstrong, Managing Director, Pilbara Standards Pty Ltd

Certification date

18th March 2022

References

ISO11459: (1997), Iron Ores- Certified reference materials – preparation and certification for use in chemical analysis.

ISO Guide 35 (2006), Reference materials – General and statistical principles for certification.

Boris Iglewicz and David Hoaglin (1993), "Volume 16: How to Detect and Handle Outliers", The ASQC Basic References in Quality Control: Statistical Techniques, Edward F. Mykytka, Ph.D., Editor.

Appendix 1

Fusion XRF Analysis. Tabulated and graphical presentation of certification data.

Appendix 2

Fusion XRF Analysis of Davis Tube Recovery Magnetic Concentrate. Tabulated and graphical presentation of certification data

Appendix 3

Laser Diffraction analysis. Tabulated and graphical presentation of certification data

Appendix 4

Wet Sieve Analysis. Tabulated and graphical presentation of certification data

Version History

Batch	Author	Document Version	Date	Modifications
PBS-71	Harry Ooi	R1	8 th August 2023	Updated certificate batch numbering format from PBS71 to PBS-71.